




CODIGO IMPA IMPA Code	D mm	L mm	PESO /Weight Kgs
673401	20	300	0,725
673402	25	300	1,02
673403	30	300	1,55
673405	40	400	3,40
673407	50	400	6,00
673409	60	400	8,70
673411	70	400	12,5
673413	80	400	16,0
673415	90	400	20,0
673417	100	400	25,0

* Otras medidas bajo consulta / Other sizes on request

U.S. MIL Spec. A18.001 K
ANALISIS QUIMICO
Chemical Analysis

Al	Cd	Zn
%	%	%
0,10 - 0,50	0,025-0,07	Resto/Rest

IMPUREZAS MAXIMAS
Maximum Impurities

Fe	Cu	Pb
%	%	%
0,005	0,005	0,006

DATOS TECNICOS / Technical data

CAPACIDAD / Capacity	781 Ah/Kg
EFICIENCIA / Efficiency	95% Teóricam. para Zinc puro / 95% Theoretically for pure Zinc
CONSUMO / Consumption	11,2 Kg/año / 11,2 Kg/Year
TENSION DE CONDUCCION/ Conduction Tension	0,23 V sobre acero polarizado / 0,23 V on polarized iron
DENSIDAD / Density	7,13 Kg/dm ³
POTENCIAL EN CIRCUITO CERRADO/Potential in closed circuit	- 0,85 V Vs electrode Ag/AgCl